

## PRODUCT DESCRIPTION

LOCTITE® UK 3173 Polyurethane Resin is a resin that is designed to be mixed with LOCTITE® UK 3182 Polyurethane Hardener. This mixture forms a low shrinkage, low exotherm potting compound.

## PROPERTIES OF UNCURED MATERIAL (Resin)

	Typical Value
Chemical Type	Polyurethane resin
Appearance	Dark brown
Viscosity, Spindle #1 @ 20 RPM, cP (25°C)	75
Specific Gravity	1.23

## PROPERTIES OF UNCURED MATERIAL (Hardener)

	Typical Value
Chemical Type	Polyurethane hardener
Appearance (mixed)	Black (black)
Viscosity, Spindle #6 @ 20 RPM, cP (25°C)	30,000
Specific Gravity	1.59

## PROPERTIES OF CURED MATERIAL

	Typical Value
Vol. Mix Ratio, Resin:Hardener	1 to 5.2
Weight Mix Ratio, Resin:Hardener	13 to 87
Mixed Specific Gravity	1.56
Mixed Viscosity, Spindle 5 @ 20 RPM (25°C) cP	5,500
Work Time, 300g (25°C)	< 7 min
Gel Time, 300g (25°C)	14 min
Regular Cure Schedule (25°C)	90 min
Alternate Cure Schedule (85°C)	30 min
Tg, °C, ASTM E1545-95a	-10
CTE, above Tg, (mm/mm°C), ASTM E831	128 E-06
Hardness, Shore A, ASTM D2240	75

## Electrical Properties

Dielectric Constant, ASTM D150	
0.1 kHz	4.68
1.0 kHz	4.02
10.0 kHz	3.76
100 kHz	3.63

Dissipation Factor, ASTM D150	
0.1 kHz	0.13
1.0 kHz	0.07
10.0 kHz	0.04
100 kHz	0.02

Insulation Resistance, ohms, ASTM D257	2.5 E13
Volume Resistivity, Ω.cm, ASTM D257	1.5 E15
Dielectric Strength, Volts/mil, ASTM D149	370

## GENERAL INFORMATION

**This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected for use with chlorine or other strong oxidizing materials.**

**For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).**

## Storage

Product shall be ideally stored in a cool, dry location in unopened containers at a temperature between 8°C to 28°C (46°F to 82°F) unless otherwise labeled. Optimal storage is at 0°C (32°F) or less. To prevent contamination of unused product, do not return any material to its original container. For further specific shelf life information, contact your local Technical Service Center.

## Data Ranges

The data contained herein may be reported as a typical value and/or range. Values are based on actual test data and are verified on a periodic basis.

## Properties of Uncured Material

	Specific Gravity	Viscosity (25°C)	Color	Mixed Color
Loctite UK 3173 Polyurethane Resin	1.24	75	Dark brown	
<b>Loctite UK 3182 Polyurethane Hardener</b>	1.59	30,000	Black	Black
<b>Loctite UK 3183 Polyurethane Hardener</b>	0.96	800	Opaque Black	Opaque Black
<b>Loctite UK 3184 Polyurethane Hardener</b>	1.46	14,000	Opaque White	Opaque tan

## Curing Properties of the Systems

(All Properties in Conjunction with LOCTITE UK 3173 Polyurethane Resin)

Hardener	Vol. Mix Ratio <i>Resin:Hardener</i>	Weight Mix Ratio <i>Resin:Hardener</i>	Mixed Specific Gravity	Mixed Viscosity, cP (25°C)	Work Time (25°C, 77°F) sample size noted	Gel Time (25°C, 77°F) sample size noted	Regular Cure Schedule (25°C, 77°F)	Alternate Cure Schedule (66°C, 150°F)
Loctite UK 3182 Polyurethane Hardener	1 to 5.2	13 to 87	1.56	5,500	< 7 min/300g	14 min/300 gm	90 min	30 min 185 F
Loctite UK 3183 Polyurethane Hardener	1 to 3.01	30 to 70	1.06	450	20 to 40min/105g	40-70 min/105 gm	24 hr	1 – 3 hours 185°F
Loctite UK 3184 Polyurethane Hardener	1 to 4.81	15 to 85	1.40	2,250	45 min/300g	150 min/300 gm	24 hr	1 – 3 hours 185°F

## Cured Properties of the System

(All Properties in Conjunction with LOCTITE UK 3173 Polyurethane Resin)

Hardener	Tg, °C	CTE above Tg (mm/mm °C)	Hardness Shore A
Loctite UK 3182 Polyurethane Hardener	-10	128 E-06	75
Loctite UK 3183 Polyurethane Hardener	-16	190 E-06	70
Loctite UK 3184 Polyurethane Hardener	-15	151 E-06	80

## Electrical Properties of the System

Dielectric Constant				
Hardener	Frequency			
	0.1 KHz	1.0 KHz	10 KHz	100 KHz
Loctite UK 3182	4.68	4.02	3.76	3.63
Loctite UK 3183	5.92	4.36	3.65	3.31
Loctite UK 3184	4.51	4.29	3.94	3.56

Dissipation Factor				
Hardener	Frequency			
	0.1 KHz	1.0 KHz	10 KHz	100 KHz
Loctite UK 3182	0.13	0.07	0.04	0.02
Loctite UK 3183	0.22	0.17	0.10	0.05
Loctite UK 3184	0.02	0.04	0.06	0.07

Hardener	Insulation Resistance, ohms	Volume Resistivity, Ω.cm	Dielectric Strength, Volts/mil
Loctite UK 3182	2.5 E13	1.5 E15	370
Loctite UK 3183	1.1 E11	6.83 E12	375
Loctite UK 3184	1.1 E12	6.61 E12	370

**Note**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada, Inc. the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned

product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**Trademark usage**

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.